

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
9 December 2004 (09.12.2004)

PCT

(10) International Publication Number
WO 2004/106476 A1

(51) International Patent Classification⁷: C11D 3/02, 3/12

(21) International Application Number:
PCT/GB2004/002176

(22) International Filing Date: 19 May 2004 (19.05.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0312143.1 28 May 2003 (28.05.2003) GB

(71) Applicant (for all designated States except MN, US):
RECKITT BENCKISER N.V. [NL/NL]; Kantoorge-
bouw de Appelaer, De Fruittuinen 2-12, NL-2132 NZ
Hoofddorp (NL).

(71) Applicant (for MN only): **RECKITT BENCKISER (UK)
LIMITED** [GB/GB]; 103-105 Bath Road, Slough, Berk-
shire SL1 3UH (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **HAHN, Karlheinz,
Ulrich, Gerhard** [DE/DE]; Reckitt Benckiser Produktions
GmbH, Benckiserplatz 1, 67059 Ludwigshafen (DE).

(74) Agents: **BOWERS, Craig, M. et al.**; Reckitt Benckiser
plc, Group Patents Department, Dansom Lane, Hull HU8
7DS (GB).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii)) for all designations
- of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



WO 2004/106476 A1

(54) Title: COMPOSITION FOR THE PROTECTION OF GLASSWARE IN A DISHWASHING PROCESS

(57) Abstract: The present invention provides a composition. The composition comprises zinc and bismuth. The composition is for use in the protection of glassware in an automatic dishwashing process.

COMPOSITION FOR THE PROTECTION OF GLASSWARE IN A DISHWASHING PROCESS

The present invention relates to a composition comprising zinc and bismuth for use in the protection of glassware in an automatic dishwasher process.

The problem of glassware corrosion in automatic dishwasher processes is well recognised. It has been put forward that the problem of glassware corrosion is the result of two separate phenomena. Firstly, it is suggested that the corrosion is due to leakage of minerals from the glass network, accompanied by hydrolysis of the silicate network. Secondly, silicate material is suggested to be released from the glass.

These phenomena can cause damage to glassware after a number of separate wash cycles. The damage may include cloudiness, scratches, streaks and other discoloration / detrimental effects.

Silicate materials have been suggested to be effective in preventing materials from being released by the glass composition. However, the use of silicate compounds can have detrimental side effects, such as the tendency to increase separation of silicate material at the glass surface.

A further solution has been to use zinc, either in metallic form (such as described in US Patent No. 3,677,820) or in the form of compounds. The use of soluble zinc compounds in the prevention of glassware corrosion in a dishwasher is described in, for example, US Patent No. 3,255,117.

However, the use of soluble zinc compounds can give rise to detrimental side effects, such as the development of a precipitate of insoluble zinc compounds formed by interaction with other species typically present in the dishwasher wash liquor. This has meant that often insoluble (or rather sparingly soluble) zinc compounds are preferred as the source of zinc in the dishwasher wash liquor. European Patents; EP-A-0 383 480, EP-A-0 383 482 and EP-A-0 387 997) describe the use of water insoluble compounds including zinc silicate, zinc carbonate, basic zinc carbonate ($\text{Zn}_2(\text{OH})_2\text{CO}_3$), zinc hydroxide, zinc oxalate, zinc monophosphate ($\text{Zn}_3(\text{PO}_4)_2$) and zinc pyrophosphate ($\text{Zn}_2\text{P}_2\text{O}_7$) for this purpose.

As these zinc compounds have only a low solubility in water it is usual that the compounds are required to have a relatively high surface area, achieved by having a small particle size, in order to attempt to achieve a sufficient concentration in water to obtain the required glass corrosion prevention effect. In this regard EP-A-0 383 480 and EP-A-0 387 997 specify that the zinc compound should have a particle size of lower than $250\mu\text{m}$, whereas EP-A-0 383 482 specifies a particle size of lower than 1.7mm . However, the use of a small particle size has not been found to overcome the delivery issue and thus, with the use of these insoluble compounds, the problem of glass corrosion effects remain.

The use of glasses and ceramics containing zinc has been found to address the problem of glassware corrosion in a

dishwasher. WO-A-01/64823 describes the use of a ceramic composition comprising zinc to protect glassware in an automatic dishwashing process. GB-A-2 372 500 and WO-A-00/39259 describe the use of a soluble glass composition comprising zinc (present in the form of ions) to protect glassware in an automatic dishwashing process. The use of a ceramic / glass zinc containing composition overcomes the problems of poor solubility / precipitation described above whilst offering effective glassware protection.

However, there is still a problem associated with the ceramic / glass zinc containing compositions (and also with water soluble / insoluble zinc compounds) in that these compositions do not perform satisfactorily in the prevention of decorated glassware corrosion.

Glassware (and also other crockery such as plates) may be decorated with a glaze to apply a pattern or design to the glassware / crockery. The glaze typically comprises an admixture of materials, similar to the admixture used in glass preparation, usually further comprising a metal oxide (such as lead oxide) / other compound to give the glaze a colour.

The glaze is usually applied to the glass in a second annealing firing process, normally at a lower temperature than the glass firing process. It is recognised that the lower firing temperature provides the glaze with a lower resilience / higher sensitivity to, for example, dishwashing conditions.

The glaze of decorated glassware / crockery can still suffer from corrosion, even in the presence of a zinc compound. Glaze corrosion has the effect of removing a portion of the glaze from the glassware / crockery over a number of dishwasher cycles. The glaze removal has the effect that the applied patterns lose their shine and the pattern colours fade. As glazes are commonly used on premium glassware products, such as handmade items, consumers washing these products are wary of washing glazed items in a dishwasher. Glazed product manufacturers are also wary of recommending the use of automatic dishwashing for cleaning these products. This can mean that the consumer has no alternative but to wash such glazed glassware / crockery by hand.

Bismuth has been used as an additive to aid the prevention of corrosion of glazed glassware corrosion. For example, BE 860180 describes the use of bismuth to avoid damage of decorated, glazed articles. However, the value of bismuth in this purpose has been diminished by the detrimental effects that the use of bismuth compound has on other components of the washing process. In this regard bismuth has been found to stain plastic materials (such as Tupperware®). Bismuth also causes the formation of a brown stain on non-decorated glassware and cutlery. Also although the glazed portion of the glassware may receive protection, bismuth has been found to stain the non-glazed portions. For these reasons the use of bismuth as a glaze protector has been avoided.

It is an object of the present invention to obviate / mitigate the problems outlined above.

According to a first aspect of the present invention there is provided a composition comprising zinc and bismuth for use in the protection of glassware in an automatic dishwashing process.

According to a second aspect of the present invention there is provided the use of a composition comprising zinc and bismuth for the protection of glassware in an automatic dishwashing process.

In the present invention it is understood that the term glassware includes items made of glass (such as drinking glasses and plates) which may be decorated (such as with a glaze and / or with etching / glass addition). The term glassware is also understood to include other items of houseware, which may comprise a material other than glass (such as a ceramic) but which have a glass / glaze coating or decoration (such as a glazed ceramic plate).

It has been found that a combination of zinc and bismuth has especially beneficial properties in the prevention of glassware corrosion in an automatic dishwashing process. Indeed not only is the composition highly effective at protecting normal glassware but also the composition has been found to be highly effective in protecting glazed glassware / crockery. Thus a single composition may now be used to provide glassware corrosion protection for both decorated glassware / crockery and non-decorated glassware in a dishwasher.

Additionally the glass protection and glaze protection effects are achieved using a lower amount of each component metal than has previously been considered necessary. Namely, normal glass protection is now possible using a much lower amount of zinc that has been previously necessary (typically half the amount), when the zinc is used in combination with bismuth. Also, glazed glass protection has now been made possible using a much lower amount of bismuth that has been previously necessary (typically half the amount), when the bismuth is used in combination with zinc.

Due to the reduction of the amount of materials needed several further advantages are realised. Firstly, the cost of use of each material is lowered. Secondly the previously observed problems caused by the use of bismuth in an automatic dishwashing process can now be avoided. Thirdly the lower amount of each material means that the use of the composition has lower environmental impact and has less stringent regulations for packaging and consumer awareness. Fourthly, as soluble zinc and bismuth compounds has been found to reduce the effect of bleach on, for example, tea-cleaning performance, by reducing the zinc and bismuth amount this detrimental effect is drastically reduced.

The ratio of zinc to bismuth in the composition is preferably in the range from 1:100 to 100:1 (based on mass of the metals). More preferably the ratio of zinc to bismuth in the composition (by mass) is from 1:10 to 10:1, more preferably from 1:5 to 5:1 and most preferably about 1:1.

Bearing the ratios outlined above in mind, the amount of zinc and bismuth provided to a dishwasher cycle is preferably from 1 to 1000 mg, more preferably from 1 to 500mg, more preferably from 1 to 200mg and more preferably 5 to 100mg. Preferably this weight refers to the combined weight of both metals.

Most preferably the zinc and bismuth are available as ions in the dishwasher washing liquor.

The zinc and bismuth may be in any suitable form to provide ions in the dishwasher liquid.

One example of a suitable form is the use of a metallic form of the metals. This form may be as separate forms of each metal disposed within the dishwasher. Such forms have been found to be solubilised over a number of wash cycles, to provide soluble ions of bismuth and zinc. The metal form may also comprise an admixture (such as an alloy) of zinc and bismuth. The alloy may contain further elements, such as other metal elements necessary to ensure stability / solubility of the alloy.

Preferred physical forms of the metal / alloy include sheets, perforated sheets, fibres, granules, powders, blocks (e.g. cuboid) or an admixture thereof.

Another example of a suitable form is the use of a salt or compound of one or both of bismuth and zinc. Most preferably the salt / compound is one which has an appreciable solubility in the washing liquor so that the effect of the zinc and bismuth can be observed. However, a salt of ei-

ther element which only has a low solubility may also be used. In the latter case (as when a metallic form of one or more of the elements themselves is used) the amount of salt / compound which is used in the dishwasher may be increased accordingly to counter the low solubility of the low solubility salts.

Most preferably the salt / compound does not contain a component which is aggressive / detrimental to the dishwasher / dishwasher contents. In the case where the salt / compound is ionic it is preferred that the salt / compound is free from chloride anions which are recognised to have a detrimental effect on dishwashers (more particularly on stainless steel dishwasher components).

Preferred examples of soluble metal salts include compounds with anions such as nitrate, sulphate, halide (especially fluoride), phosphate (where soluble), carbonate and carboxylate (such as the anions from C₁-C₁₀ mono or multi carboxy function containing carboxylic acids, especially acetate and citrate).

Preferred examples of metal compounds having a lower solubility include the oxides of the metals.

An admixture of more than one compound may be used. Also a different compound of each metal may be used.

Most preferably the salt / compound is part of a detergent formulation. The detergent formulation may comprise a rinse aid.

The detergent formulation may be any common detergent formulation of the type which are usually employed with dishwashers. The formulation may comprise a liquid, gel, powder or tablet formulation. Where the formulation is a liquid / gel generally the zinc and bismuth will be present in solution within the liquid / gel. However, it is also contemplated to have the zinc and bismuth present in the liquid /gel in the form of an insoluble salt /compound so that the zinc / bismuth may comprise a suspended particle (e.g. such as a "speckle" typically found in these formulations).

The detergent formulation normally comprises other components which are typically found in dishwasher detergent formulations. In this regard the detergent formulation typically comprises one or more components selected from the group comprising surfactants (non-ionic, anionic, cationic and zwitterionic), builders, enzymes, foam suppressants, bleaches, bleach activators, thickeners, perfumes and dyes.

It is most preferred that when the bismuth and zinc are present together in a dishwasher detergent formulation, the metals comprise from 0.002 to 6wt% (based on the weight of both metals) of the detergent formulation. More preferably the metals comprise from 0.01 to 3wt% and most preferably from 0.02 to 1.3wt% of the dishwasher detergent formulation (e.g. 0.4wt% for a 20 g tablet).

In the case of a rinse aid, especially when the rinse aid is the only source of bismuth and zinc for the dishwasher, it is preferred that the metals comprise from 0.03 to 30wt% (based on the weight of both metals) of the rinse aid for-

mulation. More preferably the metals comprise from 0.15 to 15wt% and most preferably from 0.3 to 7wt% of the rinse aid formulation.

The zinc and bismuth may also be present in a soluble ceramic / glass formulation. The glass / ceramic may contain a glass forming material such as silica (SiO_2), an alkali / alkaline metal oxide (e.g. Na_2O) and a phosphorus oxide (e.g. P_2O_5)

The glass / ceramic may comprise a homogenous body or in the alternative may be ground / crushed. Where the glass / ceramic is ground or crushed it preferably has an average particle size of less than $500\mu\text{m}$.

It will also be appreciated that for all the forms of the bismuth and zinc mentioned above an admixture of different forms, wherein each metal is present in a different physical format may be used.

In this regard it is also possible that one of the metals may be present in an additive whilst the other metal may be present in a detergent / rinse-aid formulation. As an example the zinc may be present in the dishwasher detergent / rinse-aid together with one or more other detergent components whilst the bismuth may be added as a separate additive such as a glass composition which is disposed within the dishwasher machine. Clearly other combinations of physical forms which satisfy the requirement that both bismuth and zinc are supplied to the wash liquor in accordance with the present invention.

The invention is now further described with reference to the following non-limiting Examples.

Examples - Soluble Zinc / Bismuth Compounds*

*using 'S' as a post-script

In these Examples the following detergent composition (as shown in Table 1) was used as a detergent formulation base.

Table 1

Component	%
Sodium Tripolyphosphate	48.0
Sodium Carbonate	38.8
Dye	1.0
Sodium Percarbonate	6.0
TAED	2.0
Protease	1.3
Amylase	0.4
Non-ionic Surfactant	1.0
Benzotriazole	0.25
Perfume	0.15

Test Method

In the Examples test glasses were washed 50 to 100 times in a special endurance test dishwasher (Miele G 540 Special).

Cleaning Dosage: 20g of the base detergent described above, further including bismuth and zinc in the Examples according to the invention (with the amount specified in the Examples) and with alternative additives (component and amount specified) in the comparative Examples. Automatic dosing at the beginning of the cleaning cycle.

Water Hardness in the machine: 0.1dGH, central softening through ion exchangers, internal ion exchangers not in operation.

Cleaning program 65°C (both the cleaning and the rinse cycle were operated at 65°C).

Water consumption per cycle: 23.5 litres.

There was no soiling of the glassware tested.

The test report comprised the following types of glass:

Clear Glasses

Luigi Bormoli (Italy):

"linea Michelangelo David" C32 Whitewine glass 19 cl.

Royal Leerdam (Holland):

"Fiori" Whitewine glass 19 cl.

Arc-International (France):

"Luminarc Octime Transparent", Whisky glass 30cl.

"Longchamp", 17cl, Stemglass, lead crystal glass.

"Arcoroc Elegance", Wineglass, 14,5 cl.

Ruhr Kristall Glas (Germany):

"Kölner Stange", 24cl, beer glass.

"RKG Bier", Beer Stemware, 38 cl.

Nachtmann Bleikristallwerke (Germany):

"Longdrink-glass", special edition (dishwasher sensitive),
produced especially for Reckitt Benckiser.

Decorated Glassware

Ruhr Kristall Glas (Germany):

"Snoopy Look In", Longdrink Nordland 28 cl.

"Teddy", Primusbecher 16 cl.

Arc-International (France):

"Kenia", dinner plate, 19,5 cm.

The weight loss was determined gravimetrically after 50 to 100 test washes. Visible changes to the glass surface were evaluated in natural light or in a special light box. The dimensions of the light box were 70cm x 40cm x 65cm (l x b x h) and the inside of the box was painted matt black. The box was lit from above with an L 20w/25S (60cm long) Osram lamp, which was covered in front with a screen. Shelves

were disposed in the box on which the glasses were placed for evaluation. The box was open at the front.

The glass corrosion was evaluated using the following criteria; glass clouding (GC), line corrosion (CL) and decoration damage (DS). The parameters glass clouding and line corrosion were used for the non-decorated glasses and the parameter decoration damage for the decorated glasses. For each parameter a score was given in accordance with the table below.

Evaluation	Damage Impact
0	No glass damage
1	First minor damage / hardly visible
2	Slight damage, visible to expert or in the light box
3	Visible damage
4	Strong damage, clearly visible

Comparative Example 1(S)

In this Comparative Example only zinc was added to the base detergent formulation. The zinc was present at 0.4% by weight (based upon zinc), as zinc sulphate mono-hydrate $\text{ZnSO}_4 \cdot \text{H}_2\text{O}$.

The results of the tests are shown in Table 2a (Glass Corrosion) and Table 2b (Mass Loss).

Table 2a - Glass Corrosion

Glasses	50 cycles		100 Cycles	
	GC	CL	GC	CL
Michelangelo	0.5	2.0	2.0	3.0
Octime	2.5	2.0	2.5	2.5
Longchamp	1.0	2.0	2.0	2.5
RKG Kölsch	1.5	2.0	1.0	2.0
RKG Bier	2.5	2.0	2.5	2.0
Nachtmann Longdrink	1.5	0,0	2.5	0.0
Arcoroc Elegance	2.5	0.0	2.5	2.0
<i>Average</i>	<i>1.71</i>	<i>1.43</i>	<i>2.14</i>	<i>2.00</i>
Decorated Glassware	DS		DS	
Snoopy	1.5		2.5	
Teddy	1.5		2.5	
Kenia Plates	2.0		3.0	
<i>Average</i>	<i>1.67</i>		<i>2.67</i>	

Table 2b - Mass Loss

Glasses	50 cycles Mass Loss (mg)	100 cycles Mass Loss (mg)
Michelangelo	10	20
Octime	13	27
Longchamp	22	45
RKG Kölsch	10	21
RKG Bier	18	39
Nachtmann Longdrink	25	53
Arcoroc Elegance	10	20
<i>Sum</i>	<i>108</i>	<i>225</i>
Decorated Glassware		
Snoopy	37	91
Teddy	12	35
Kenia Plates	28	77
<i>Sum</i>	<i>77</i>	<i>203</i>

Comparative Example 2(S)

In this Comparative Example only bismuth was added to the base detergent formulation. The bismuth was present at 0.4% by weight (based upon bismuth), as bismuth citrate.

The results of the tests are shown in Table 3a (Glass Corrosion) and Table 3b (Mass Loss).

Table 3a - Glass Corrosion

Glasses	50 cycles		100 Cycles	
	GC	CL	GC	CL
Michelangelo	1.5	2.5	0.5	3.5
Octime	2.5	2.5	2.5	3.0
Longchamp	2.5	3.0	3.5	4.0
RKG Kölsch	2.0	2.5	2.0	4.0
RKG Bier	2.5	2.5	2.5	3.5
Nachtmann Longdrink	2.5	0.0	3.5	0.0
Arcoroc Elegance	2.5	2.5	3.0	4.0
<i>Average</i>	<i>2.29</i>	<i>2.21</i>	<i>2.5</i>	<i>3.14</i>
Decorated Glassware	DS		DS	
Snoopy	0.5		1.0	
Teddy	0.5		0.5	
Kenia Plates	1.0		1.0	
<i>Average</i>	<i>0.67</i>		<i>0.83</i>	

Table 3b - Mass Loss

Glasses	50 cycles Mass Loss (mg)	100 cycles Mass Loss (mg)
Michelangelo	17	26
Octime	20	28
Longchamp	44	76
RKG Kölsch	20	33
RKG Bier	33	45
Nachtmann Longdrink	58	79
Arcoroc Elegance	17	23
<i>Sum</i>	<i>209</i>	<i>311</i>
Decorated Glassware		
Snoopy	21	28
Teddy	15	19
Kenia Plates	30	41
<i>Sum</i>	<i>66</i>	<i>88</i>

Comparative Examples 1(S) and 2(S) show that whilst zinc is able to provide corrosion protection for non-decorated glassware it offers poor protection for decorated glassware (when present in the formulation at 0.4wt%).

Conversely bismuth is able to provide corrosion protection for decorated glassware yet it offers poor protection for non-decorated glassware (when present in the formulation at 0.4wt%).

Example 1(S)

In this Example both bismuth and zinc were added to the base detergent formulation. The bismuth was present at 0.2% by weight (based upon bismuth), as bismuth citrate. The zinc was present at 0.2% by weight (based upon zinc), as zinc citrate.

The results of the tests are shown in Table 4a (Glass Corrosion) and Table 4b (Mass Loss).

Table 4a - Glass Corrosion

Glasses	50 cycles		100 Cycles	
	GC	CL	GC	CL
Michelangelo	1.0	1.0	1.5	2.0
Octime	2.0	1.5	2.0	2.0
Longchamp	2.0	2.0	2.5	2.5
RKG Kölsch	0.0	1.5	1.0	2.0
RKG Bier	1.5	2.0	2.0	2.0
Nachtmann Longdrink	2.5	0.0	3.0	0.0
Arcoroc Elegance	2.0	2.0	2.5	2.5
<i>Average</i>	<i>1.57</i>	<i>1.43</i>	<i>2.07</i>	<i>1.86</i>
Decorated Glassware	DS		DS	
Snoopy	0.0		0.5	
Teddy	0.5		1.0	
Kenia Plates	0.5		0.5	
<i>Average</i>	<i>0.33</i>		<i>0.67</i>	

Table 4b - Mass Loss

Glasses	50 cycles Mass Loss (mg)	100 cycles Mass Loss (mg)
Michelangelo	18	27
Octime	10	16
Longchamp	16	33
RKG Kölsch	10	23
RKG Bier	11	27
Nachtmann Longdrink	21	54
Arcoroc Elegance	13	18
<i>Sum</i>	<i>100</i>	<i>199</i>
Decorated Glassware		
Snoopy	14	29
Teddy	7	17
Kenia Plates	24	41
<i>Sum</i>	<i>45</i>	<i>87</i>

In contrast to Comparative Examples 1(S) and 2(S), Example 1(S) surprisingly shows that a formulation containing a combination of zinc and bismuth (both present at 0.2wt%) provides equal / better non-decorated glassware corrosion protection (when compared to 0.4wt% zinc). Additionally the combination of zinc and bismuth provides equal decorated glassware corrosion protection (when compared to 0.4wt% bismuth).

These effects are both unexpected.

Thus, it has been shown that, with the inclusion of 0.2wt% bismuth, the amount of zinc incorporated in a detergent formulation can be reduced by half (0.4wt% to 0.2wt%), yet the same amount of non-decorated glassware corrosion protection is still achieved. The same situation reduction applies for bismuth and decorated glassware with the incorporation of zinc.

Additionally the composition offers protection for both non-decorated and decorated glassware.

Examples - Metallic Zinc / Bismuth*

*using 'M' as a post-script

In these Examples the following detergent composition (as shown in Table 5) was used as a detergent formulation base.

Table 5

Component	%
Sodium Tripolyphosphate	45.0
Sodium Carbonate	18.5
Sodium Bicarbonate	2.0
Dye	0.15
Sodium Perborate	10.0
TAED	2.0
Protease	1.5
Amylase	0.5
Non-ionic Surfactant	3.5
Polyethylene Glycol	7.5
Benzotriazole	0.25
Perfume	0.15

Test Method, Glasses, Damage Evaluation

As for the soluble zinc/bismuth compounds.

Comparative Example 1 (M)

In this Example only zinc was added to the base detergent formulation. The zinc was present at 0.06g per cycle, in the form of a sheet of metallic zinc (13mm x 6mm x 1mm, mass 60g, mass loss 6g over 100 cycles).

The results of the tests are shown in Table 6a (Glass Corrosion) and Table 6b (Mass Loss).

Table 6a - Glass Corrosion

Glasses	100 Cycles	
	GC	CL
Octime	0.5	2.5
Longchamp	2.0	3.5
RKG Kölsch	1.0	3.0
Fiori	1.0	3.5
Nachtmann Longdrink	3.5	0.0
Arcoroc Elegance	3.0	3.5
<i>Average</i>	<i>1.83</i>	<i>2.67</i>
Decorated Glassware	DS	
Snoopy	3.0	
Teddy	3.0	
Kenia Plates	4.0	
<i>Average</i>	<i>3.33</i>	

Table 6b - Mass Loss

Glasses	100 cycles Mass Loss (mg)
Octime	37.5
Longchamp	73
RKG Kölsch	47
Fiori	31
Nachtmann Longdrink	103
Arcoroc Elegance	29
<i>Sum</i>	<i>320.5</i>
Decorated Glassware	
Snoopy	276
Teddy	85
Kenia Plates	160
<i>Sum</i>	<i>521</i>

Comparative Example 2 (M)

In this Example only bismuth was added to the base detergent formulation. The bismuth was present at 0.2g per cycle, as fine metallic bismuth dust.

The results of the tests are shown in Table 7a (Glass Corrosion) and Table 7b (Mass Loss).

Table 7a - Glass Corrosion

Glasses	100 Cycles	
	GC	CL
Octime	1.5	4.0
Longchamp	3.5	3.5
RKG Kölsch	2.0	4.0
Fiori	1.5	4.0
Nachtmann Longdrink	3.0	0.0
Arcoroc Elegance	3.5	4.0
<i>Average</i>	2.5	3.25
Decorated Glassware	DS	
Snoopy	3.5	
Teddy	3.0	
Kenia Plates	4.0	
<i>Average</i>	3.5	

Table 7b - Mass Loss

Glasses	100 cycles Mass Loss (mg)
Octime	75.5
Longchamp	204
RKG Kölsch	90
Fiori	59
Nachtmann Longdrink	288
Arcoroc Elegance	64
<i>Sum</i>	<i>780.5</i>
Decorated Glassware	
Snoopy	413
Teddy	195
Kenia Plates	271
<i>Sum</i>	<i>879</i>

Comparative Example 3(M)

In this Example no bismuth nor zinc was added to the base detergent formulation.

The results of the tests are shown in Table 8a (Glass Corrosion) and Table 8b (Mass Loss).

Table 8a - Glass Corrosion

Glasses	100 Cycles	
	GC	CL
Octime	1.5	3.5
Longchamp	3.0	3.5
RKG Kölsch	2.0	4.0
Fiori	1.5	4.0
Nachtmann Longdrink	3.0	0.0
Arcoroc Elegance	4.0	4.0
<i>Average</i>	<i>2.5</i>	<i>3.17</i>
Decorated Glassware	DS	
Snoopy	3.5	
Teddy	3.5	
Kenia Plates	4.0	
<i>Average</i>	<i>3.67</i>	

Table 8b - Mass Loss

Glasses	100 cycles Mass Loss (mg)
Octime	78
Longchamp	210
RKG Kölsch	88
Fiori	86
Nachtmann Longdrink	242
Arcoroc Elegance	71
<i>Sum</i>	<i>775</i>
Decorated Glassware	
Snoopy	549
Teddy	151
Kenia Plates	276
<i>Sum</i>	<i>976</i>

Comparative Examples 1(M), 2(M) and 3(M) show that whilst metallic zinc is able to provide corrosion protection for non-decorated glassware it offers poor protection for decorated glassware.

Metallic bismuth offers poor protection for decorated and non-decorated glassware.

Example 1 (M)

In this Example both bismuth and zinc were added to the base detergent formulation. The bismuth was present at 0.2g per cycle, as fine metallic bismuth dust. The zinc was present at 0.06g per cycle, in the form of a sheet of metallic zinc (13mm x 6mm x 1mm, mass 60g, mass loss 6g over 100 cycles).

The results of the tests are shown in Table 9a (Glass Corrosion) and Table 9b (Mass Loss).

Table 9a - Glass Corrosion

Glasses	100 Cycles	
	GC	CL
Octime	0.5	2.5
Longchamp	2.5	3.0
RKG Kölsch	1.0	2.5
Fiori	0.5	3.0
Nachtmann Longdrink	2.5	0.0
Arcoroc Elegance	2.5	3.0
<i>Average</i>	<i>1.58</i>	<i>2.33</i>
Decorated Glassware	DS	
Snoopy	2.5	
Teddy	2.5	
Kenia Plates	3.0	
<i>Average</i>	<i>2.67</i>	

Table 9b - Mass Loss

Glasses	100 cycles Mass Loss (mg)
Octime	25
Longchamp	69
RKG Kölsch	41
Fiori	29
Nachtmann Longdrink	92
Arcoroc Elegance	27
<i>Sum</i>	283
Decorated Glassware	
Snoopy	181
Teddy	76
Kenia Plates	118
<i>Sum</i>	375

In contrast to Comparative Examples 1(M), 2(M) and 3(M), Example 1(M) surprisingly shows that a formulation containing a combination of metallic zinc and bismuth provides enhanced non-decorated glassware corrosion protection (when compared to only one of the metals). Additionally the combination of zinc and bismuth provides enhanced decorated glassware corrosion protection (when compared to only one of the metals).

These effects are both unexpected.

CLAIMS

1. A composition comprising zinc and bismuth for use in the protection of glassware in an automatic dishwashing process.
2. A composition according to claim 1, wherein the ratio of zinc to bismuth in the composition is from 1:100 to 100:1 (based on mass of the metals).
3. A composition according to claim 2, wherein the ratio of zinc to bismuth in the composition (by mass) is from 1:10 to 10:1, more preferably from 1:5 to 5:1 and most preferably about 1:1.
4. A composition according to claim 1,2 or 3, wherein the zinc and / or bismuth are in metallic form.
5. A composition according to claim 4, wherein the metallic form is an alloy of zinc and bismuth.
6. A composition according to claim 1,2 or 3, wherein the zinc and / or bismuth are present as a salt or compound.
7. A composition according to claim 6, wherein the salt / compound is a nitrate, oxide, sulphate, phosphate, halide, carbonate or carboxylate salt.
8. A composition according to any one of claims 1 to 7, wherein the composition comprises a detergent formulation.

9. A composition according to claim 8, wherein the bismuth and zinc comprise from 0.002wt% to 6wt% (based on the weight of both metals) of the detergent formulation.
10. A composition according to claim 9, wherein the bismuth and zinc comprise from 0.01 to 3wt% and most preferably from 0.02 to 1.3wt% (e.g. 0.4wt%) of the detergent formulation.
11. A composition according to any one of claims 1 to 7, wherein the composition comprises a rinse aid formulation.
12. A composition according to claim 11, wherein the bismuth and zinc comprise from 0.03wt% to 30wt%, more preferably 0.15 to 15 % and most preferable 0.3 to 7 % (based on the weight of both metals) of the rinse aid formulation
13. A composition according to any one of claims 1 to 7, wherein the composition comprises a soluble ceramic / glass formulation.
14. The use of a composition comprising zinc and bismuth for the protection of glassware in an automatic dishwashing process.
15. The use according to claim 14, wherein the amount of zinc and bismuth provided to a dishwasher cycle is from 1 to 1000mg.
16. The use according to claim 15, wherein the amount of zinc and bismuth provided to a dishwasher cycle is from 5 to 500mg.

17. The use according to claim 16, wherein 5 to 100 mg zinc and 5 to 100 mg bismuth is provided to a dishwasher cycle.

INTERNATIONAL SEARCH REPORT

International Application No
/GB2004/002176

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C11D3/02 C11D3/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 070 587 A (PROCTER & GAMBLE) 26 January 1983 (1983-01-26) page 10, line 10 - line 20; claim 1	1-3, 6-12, 14
A	GB 1 586 067 A (PROCTER & GAMBLE) 18 March 1981 (1981-03-18) page 1, line 32 - line 35; claims	1, 6-10, 14
A	EP 0 383 482 A (PROCTER & GAMBLE) 22 August 1990 (1990-08-22) cited in the application page 2, lines 1-5; claims	1, 6-10, 14
A	GB 2 372 500 A (RECKITT BENCKISER NV) 28 August 2002 (2002-08-28) cited in the application claims	1, 6, 13, 14
	----- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

10 September 2004

Date of mailing of the international search report

20/09/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Grittern, A

INTERNATIONAL SEARCH REPORT

International Application No

/GB2004/002176

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2 425 907 A (BACON LESLIE R. ET AL) 19 August 1947 (1947-08-19) column 1, line 1 - line 15; claim 1 -----	1, 14

INTERNATIONAL SEARCH REPORT

International Application No
/GB2004/002176

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0070587	A	26-01-1983	AT 16403 T	15-11-1985
			CA 1174553 A1	18-09-1984
			DE 3267272 D1	12-12-1985
			EP 0070587 A1	26-01-1983
			US 4443270 A	17-04-1984
GB 1586067	A	18-03-1981	BE 860180 A2	27-04-1978
			DE 2747602 A1	03-05-1978
			FR 2369337 A1	26-05-1978
			IT 1143765 B	22-10-1986
			NL 7711867 A	03-05-1978
EP 0383482	A	22-08-1990	US 4917812 A	17-04-1990
			AT 141322 T	15-08-1996
			AU 639684 B2	05-08-1993
			AU 4934390 A	16-08-1990
			CA 2009048 A1	13-08-1990
			DE 69028028 D1	19-09-1996
			DE 69028028 T2	06-03-1997
			EP 0383482 A2	22-08-1990
			ES 2090092 T3	16-10-1996
			JP 2289700 A	29-11-1990
			NZ 232479 A	23-12-1992
GB 2372500	A	28-08-2002	CA 2438869 A1	06-09-2002
			EP 1404623 A2	07-04-2004
			WO 02068352 A2	06-09-2002
US 2425907	A	NONE		